



US012503627B2

(12) **United States Patent**  
**Liao et al.**

(10) **Patent No.:** **US 12,503,627 B2**

(45) **Date of Patent:** **Dec. 23, 2025**

(54) **POLYOLEFIN BONDING ADHESIVE FILM**

(71) Applicant: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(72) Inventors: **Te-Chao Liao**, Taipei (TW);  
**Ching-Yao Yuan**, Taipei (TW);  
**Chih-Feng Wang**, Taipei (TW);  
**Teng-Ko Ma**, Taipei (TW)

(73) Assignee: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 320 days.

(21) Appl. No.: **18/297,631**

(22) Filed: **Apr. 9, 2023**

(65) **Prior Publication Data**  
US 2024/0191104 A1 Jun. 13, 2024

(30) **Foreign Application Priority Data**  
Dec. 13, 2022 (TW) ..... 111147680

(51) **Int. Cl.**  
**C09J 7/38** (2018.01)  
**B32B 7/12** (2006.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **C09J 7/381** (2018.01); **B32B 7/12** (2013.01); **B32B 15/085** (2013.01); **B32B 15/20** (2013.01); **B32B 27/08** (2013.01); **B32B 27/30** (2013.01); **B32B 27/32** (2013.01); **B65D 65/40** (2013.01); **C09J 5/06** (2013.01); **C09J 7/243** (2018.01); **C09J 7/35** (2018.01); **B32B 2250/24** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC ..... C09J 7/381; C09J 7/243; C09J 7/35; C09J 151/00; C09J 151/06  
See application file for complete search history.

(56) **References Cited**  
**U.S. PATENT DOCUMENTS**  
2012/0074020 A1 3/2012 Kendig et al.  
2013/0209868 A1\* 8/2013 Suzuta ..... B32B 27/32 429/176  
(Continued)

**FOREIGN PATENT DOCUMENTS**  
CN 112789174 A 5/2021  
JP 6427923 A 1/1989  
(Continued)

**OTHER PUBLICATIONS**  
JP 2019-085480 Machine Translation (Year: 2019).\*  
Astm D1238-13 (Year: 2013).\*

*Primary Examiner* — Zachary M Davis  
(74) *Attorney, Agent, or Firm* — Li & Cai Intellectual Property Office

(57) **ABSTRACT**  
A polyolefin bonding adhesive film includes a support base layer and a bonding adhesive layer formed on a side surface of the support base layer by co-extrusion. The support base layer is a polypropylene film. The bonding adhesive layer is formed of a first polyolefin copolymer modified by maleic anhydride. The first polyolefin copolymer is formed by copolymerization of at least two kinds of C2 to C4 olefin molecules, a first graft ratio of the maleic anhydride grafted onto the first polyolefin copolymer is between 0.5% and 5%, and a first melt index of the first polyolefin copolymer is between 3 g/10 min and 5 g/10 min.

**8 Claims, 2 Drawing Sheets**

