



US012576623B2

(12) **United States Patent**
Liao et al.

(10) **Patent No.:** **US 12,576,623 B2**
(45) **Date of Patent:** **Mar. 17, 2026**

(54) **PEARL PAPER STRUCTURE AND METHOD FOR MANUFACTURING THE SAME**

(71) Applicant: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(72) Inventors: **Te-Chao Liao**, Taipei (TW); **Hung-Yi Chang**, Taipei (TW); **Teng-Ko Ma**, Taipei (TW); **Wei-Tang Liao**, Taipei (TW)

(73) Assignee: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 205 days.

(21) Appl. No.: **18/610,225**

(22) Filed: **Mar. 19, 2024**

(65) **Prior Publication Data**

US 2025/0214326 A1 Jul. 3, 2025

(30) **Foreign Application Priority Data**

Dec. 28, 2023 (TW) 112151187

(51) **Int. Cl.**
B32B 27/08 (2006.01)
B29C 48/08 (2019.01)
(Continued)

(52) **U.S. Cl.**
CPC **B32B 27/08** (2013.01); **B32B 27/20** (2013.01); **B32B 27/32** (2013.01); **B29C 48/08** (2019.02); **B29C 48/21** (2019.02); **B29K 2023/06** (2013.01); **B29K 2023/12** (2013.01); **B29K 2509/00** (2013.01); **B32B 2250/03** (2013.01); **B32B 2250/242** (2013.01);
(Continued)

(58) **Field of Classification Search**

CPC B32B 27/08; B32B 27/20; B32B 27/32; B32B 2250/03; B32B 2250/242; B32B 2250/40; B32B 2264/1022; B32B 2264/104; B32B 2270/00; B32B 2307/406; B32B 2307/538; B32B 2554/00; B29C 48/08; B29C 48/21; B29K 2023/06; B29K 2023/12; B29K 2509/00; Y10T 428/24355
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

2002/0182391 A1 12/2002 Migliorini et al.
2015/0360449 A1* 12/2015 Larios B32B 5/022 428/213

FOREIGN PATENT DOCUMENTS

CN 1133535 C 1/2004
TW 201601920 A 1/2016

(Continued)

Primary Examiner — Donald M Flores, Jr.

(74) *Attorney, Agent, or Firm* — Li & Cai Intellectual Property Office

(57) **ABSTRACT**

A pearl paper structure and a method for manufacturing the same are provided. The pearl paper structure includes a middle layer and a matte layer. The matte layer is disposed on the middle layer. A material of the matte layer includes a polyolefin material and fillers. The polyolefin material is formed by reacting a polypropylene, a polyethylene, and an initiator. Based on a total weight of the matte layer being 100 wt %, an amount of the polypropylene ranges from 20 wt % to 65 wt %, an amount of the polyethylene ranges from 30 wt % to 75 wt %, and an amount of the fillers ranges from 5 wt % to 10 wt %. An arithmetic average roughness of the matte layer ranges from 0.5 μm to 1.3 μm.

14 Claims, 1 Drawing Sheet

