



US012558882B2

(12) **United States Patent**  
**Liao et al.**

(10) **Patent No.:** **US 12,558,882 B2**

(45) **Date of Patent:** **Feb. 24, 2026**

(54) **POLYOLEFIN PACKAGING MATERIAL**

(71) Applicant: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(72) Inventors: **Te-Chao Liao**, Taipei (TW);  
**Ching-Yao Yuan**, Taipei (TW);  
**Chih-Feng Wang**, Taipei (TW);  
**Teng-Ko Ma**, Taipei (TW)

(73) Assignee: **NAN YA PLASTICS CORPORATION**, Taipei (TW)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 406 days.

(21) Appl. No.: **18/296,980**

(22) Filed: **Apr. 6, 2023**

(65) **Prior Publication Data**  
US 2024/0190116 A1 Jun. 13, 2024

(30) **Foreign Application Priority Data**  
Dec. 13, 2022 (TW) ..... 111147681

(51) **Int. Cl.**  
**B32B 27/08** (2006.01)  
**B32B 7/02** (2019.01)  
(Continued)

(52) **U.S. Cl.**  
CPC ..... **B32B 27/32** (2013.01); **B32B 7/02** (2013.01); **B32B 7/12** (2013.01); **B32B 27/08** (2013.01); **B65D 65/40** (2013.01); **C09J 151/06** (2013.01); **B32B 2250/242** (2013.01); **B32B 2307/31** (2013.01); **B32B 2307/414** (2013.01); **B32B 2307/518** (2013.01);  
(Continued)

(58) **Field of Classification Search**  
CPC . B32B 27/32; B32B 7/12; B32B 27/08; C09J 151/06  
See application file for complete search history.

(56) **References Cited**  
**U.S. PATENT DOCUMENTS**  
5,139,878 A 8/1992 Kim  
5,340,917 A \* 8/1994 Eckman ..... C08J 5/00 526/943  
(Continued)

**FOREIGN PATENT DOCUMENTS**  
CN 204210108 U 3/2015  
CN 105895833 B 10/2018  
(Continued)

*Primary Examiner* — Joanna Pleszczynska  
(74) *Attorney, Agent, or Firm* — Li & Cai Intellectual Property Office

(57) **ABSTRACT**  
A polyolefin packaging material includes a first polyolefin polymer film, a second polyolefin polymer film, and a polyolefin bonding adhesive layer. The first polyolefin polymer film is a cast polypropylene film (CPP film). The second polyolefin polymer film is a biaxially oriented polypropylene film (BOPP film). The polyolefin bonding adhesive layer is bonded between the first polyolefin polymer film and the second polyolefin polymer film. The polyolefin bonding adhesive layer is formed of a polyolefin copolymer modified by maleic anhydride, the polyolefin copolymer is formed by copolymerization of at least two kinds of C2 to C4 olefin molecules, a graft ratio of the maleic anhydride grafted onto the polyolefin copolymer is between 0.5% and 5%, and a melt index of the polyolefin copolymer is between 1 g/10 min and 5 g/10 min.

**11 Claims, 3 Drawing Sheets**

100A  
↙

