

Resin Type ABS Grade Lot Number		檢測報告 CERTIFICATE OF ANALYSIS		
特性 Properties	單位 Units	條件 Conditions	測試方法 Test Method	結果 Results
IZOD衝擊強度 Izod Impact Strength	Kg-cm/cm	1/8" 23°C	ASTM-D256	10-30
流動係數 Melt Flow Index	g/10 min	220°C 10kg	ASTM-D1238	10-35
拉伸強度 Tensile Strength	Kgf/cm ²	50mm/min 1/8" 23°C	ASTM-D638	330-420
伸長率 Tensile Elongation	%	50mm/min 1/8" 23°C	ASTM-D638	20-80
抗彎強度 Flexural Strength	Kgf/cm ²	15 mm/min 1/8",23°C	ASTM-D790	550-710
彎曲模量 Flexural Modulus	Kgf/cm ²	15 mm/min 1/8",23°C	ASTM-D790	20000-23000
熱變形H.D.T Heat Deflection	°C	1/4" 120°C/hr	ASTM-D648	83-88
比重 Specific Gravity	-	23°C	ASTM-D792	1.04
耐燃性 Flammability	-	1.5mm	UL-94	HB
透光率 Transmittance	%	23°C	ASTM-D1003	-
RoHS		標準 Standard	結果 Results	
Br (溴)		< 600ppm	-	
Cr (鉻)		< 50ppm	-	
Hg (汞)		< 5ppm	-	
Pb (鉛)		< 50ppm	-	
Cd (鎘)		< 50ppm	-	
Cl (氯)		< 600ppm	-	
CIE L.a.b		L	a	b
		-	-	-
		DE		
		-		